



Document No.: NMS 219/2 Revision A, August 26, 2025

NCAMP Material Specification

*This specification is generated and maintained in accordance with NCAMP  
Standard Operating Procedures, NSP 100*

350°F Autoclave Cure, High Toughness Epoxy Prepregs  
Type 37, Class 2, Form 4, Grade 193, Style 3K-PW

Syensqo EP2190 T650 PW

Prepared by: Evelyn Lian (NCAMP/NIAR), Royal Lovingfoss (NCAMP/NIAR), Vinsensius Tanoto  
(NCAMP/NIAR)

Reviewed by: Pippin Arthur (Syensqo), Thu Nguyen (Syensqo), Phillip Lewis (Syensqo), Stuart  
Tudor-Jones (Syensqo), David Harvey (Syensqo), Ludmila Conway (Syensqo)  
and Matt Aldridge (Syensqo)

**Distribution Statement A.** Approved for public release; distribution is unlimited.

National Center for Advanced Materials Performance  
Wichita State University – NIAR  
1845 Fairmount Ave., Wichita, KS 67260-0093, USA

## REVISIONS:

Rev	By	Date	Pages Revised or Added
N/C	Evelyn Lian and Royal Lovingfoss	11/4/2021	Document Initial Release
A	Vinsensius Tanoto and Royal Lovingfoss	8/26/2025	<p>All Section:</p> <ul style="list-style-type: none"> <li>Replaced "Solvay" with "Syensqo".</li> </ul> <p>Cover Page:</p> <ul style="list-style-type: none"> <li>Added "Form 4".</li> <li>Updated reviewer names.</li> <li>Added Matt Aldridge (Syensqo).</li> </ul> <p>Section 1.3:</p> <ul style="list-style-type: none"> <li>Added "Form 4".</li> </ul> <p>Section 3:</p> <ul style="list-style-type: none"> <li>Table 1, Note 2 was added to Gel, Tack and DSC (prepreg for receiving inspection).</li> <li>Table 1, Drape, FTIR and DSC (Resin) were removed.</li> </ul> <p>Section 3.5.3:</p> <ul style="list-style-type: none"> <li>Compression RT was replaced with ET.</li> <li>Specification limits were added.</li> <li>Modulus ranges were added.</li> </ul> <p>QPL:</p> <ul style="list-style-type: none"> <li>Added "Form 4".</li> </ul>

# 1. SCOPE:

## 1.1 Form:

This detail specification along with the base specification NMS 219 establishes the requirements for carbon fiber fabric impregnated with a modified B-staged epoxy resin ("fabric prepreg"). The prepreg is produced using a hot-melt process.

This detail specification follows the section and table numbering scheme of the base specification. It contains additional or superseding requirements. The base specification shall govern where no additional requirement is specified; in such cases, the applicable sections are omitted from this detail specification.

- 1.3 Classification:** All products qualified to this detail specification have the following classification: Type 37, Class 2, Form 4, Grade 193, Style 3K-PW

## 3. TECHNICAL REQUIREMENTS:

Table 1 – Prepreg Physical and Chemical Properties

Property	Test Method <sup>(1)</sup>	Number of Replicates	Requirements <sup>(5)</sup>
Resin Content	ASTM D3529	Every roll <sup>(2)</sup>	37±3% ind. 37±2% avg.
Fiber Areal Weight	ASTM D3529	Every roll <sup>(2)</sup>	193±7 gsm ind. 193±5 gsm avg.
Volatile Content	ASTM D3530	First and last rolls of every batch <sup>(2)</sup>	2.5% max ind. 2.5% max avg.
Flow	ASTM D3531	First and last rolls of every batch <sup>(2)</sup>	9 to 18%
Gel Time <sup>(4)</sup>	ASTM D3532	First and last rolls of every batch <sup>(2)</sup>	16 to 25 mins
Tack	See 4.6.1	First and last rolls of every batch <sup>(2)</sup>	Pass
HPLC <sup>(3)</sup>	SACMA SRM 20R-94	First and last rolls of a batch	P1/P4: 0.32 - 0.38 P2/P4: 0.34 - 0.44 P3/P4: 0.005 - 0.025
Differential Scanning Calorimetry (DSC) <sup>(6)</sup>			
Exotherm peak temperature	ASTM D3418	First and last rolls of every batch <sup>(2)</sup>	231 to 240°C
Total heat of reaction <sup>(4)</sup>			127 to 157 J/g

<sup>(1)</sup> Specific procedures should be identical to those used in the original material qualification program.

<sup>(2)</sup> Three specimens should be taken across the width of the prepreg; left, center, right.

- (3) Not required for receiving inspection test.
- (4) Optional for batch release test.
- (5) "ind." refers to individual measurements. "avg." refers to the average measurements per roll.
- (6) Product Form is Prepreg.

### **3.2 Constituent Material Requirements:**

3.2.2 Reinforcement: Efforts to qualify the carbon fiber to NCAMP carbon fiber material specification, NMS 818, are ongoing. In the meantime, Syensqo will continue to provide aerospace-grade carbon fiber for this prepreg per the prepregger's carbon fiber procurement specification PRS 61658564-TX and Syensqo's internal aerospace-grade PCD. In addition, the following change control is implemented on the carbon fiber:

The carbon fiber tow product manufacturer shall establish control factors which will yield product meeting the technical requirements of this specification. The factors which are used in the production of fiber tow used in the prepreg material qualification shall constitute the approved factors; they shall be used for manufacturing production carbon fiber tow product. Control factors are Controlled Process Equipment and Controlled Process Parameters for producing the product. Control factors include, but are not limited to, the following:

- a) PAN Precursor formulation (raw ingredients and ratios),
- b) PAN Precursor manufacturing process, equipment, line, or site,
- c) PAN Precursor acceptance requirements,
- d) Carbon fiber tow processing parameters (e.g. temperature and speed),
- e) Carbon fiber tow manufacturing equipment, line, or site,
- f) Carbon fiber tow acceptance requirements,
- g) Carbon fiber tow acceptance test methods,
- h) Carbon fiber tow acceptance sampling plan,
- i) Carbon fiber tow surface treatment methods and levels,
- j) Carbon fiber tow sizing formulation and sizing level, and
- k) Carbon fiber tow sizing application and drying methods, including equipment.

If it is necessary to make any change in the above control factors, the carbon fiber tow product manufacturer shall submit for re-approval to NCAMP through the prepreg manufacturer in accordance with NRP 101 Prepreg Process Control Document (PCD) Preparation and Maintenance Guide. NRP 102 Polyacrylonitrile-based Carbon Fiber Process Control Document (PCD) Preparation and Maintenance Guide may be used as a reference. The change shall not be incorporated prior to the receipt of re-approval notice, typically in the form of a signed Advanced Change Notice (ACN).

### **3.4 Visual and Dimensional Requirements:**

3.4.4 Roll characteristics - The standard width for this product is 48 inches. Other widths may be supplied only if it is specifically requested by the purchaser.

### 3.5 Laminate (Cured Prepreg) Requirements:

#### 3.5.2 Cured Laminate Physical Properties:

TABLE 3 - Cured Laminate Physical Properties

Property	Test Method <sup>(1)</sup>	Requirements <sup>(2)</sup>
Cured Ply Thickness, CPT <sup>(3)</sup>	ASTM D3171	0.0075 to 0.0083 inch, avg.
Dry Glass Transition Temperature Dry, Tg by DMA <sup>(4)</sup>	by flexural loading per ASTM D7028	363 to 399 °F, ind.

(1) Specific procedures should be identical to those used in the original material qualification program.

(2) "ind." refers to individual measurements. "avg." refers to the average measurements per panel.

(3) Cured Ply Thickness of the Laminates in Table 4. Computed from actual qualification panel thicknesses using  $\alpha=0.01$  and modified CV, and theoretical Cured Ply Thickness as the nominal.

(4) Limits computed using Syensqo historical average production data  $\pm 18^\circ\text{F}$ . Drying at  $250^\circ\text{F} \pm 5^\circ\text{F}$  for 1 day minimum prior to testing may be required if specimens are likely to have moisture.

#### 3.5.3 Cured Laminate Mechanical Properties:

TABLE 4 - Required Cured Laminate Tests for Mechanical Properties (Class 2)

Property	Test Method <sup>(1)</sup>	Requirements <sup>(3)</sup>
90° (Fill) Tension Strength and Modulus, Room Temperature, Ambient Layup: [90] <sub>10</sub>	ASTM D3039	Strength <sup>(2)</sup> : Min. Ind. $\geq 99.41$ ksi Strength <sup>(2)</sup> : Average $\geq 113.91$ ksi Modulus <sup>(2)(4)</sup> : 8.63 to 10.16 msi, avg
90° (Fill) Compression Strength and Modulus, 250°F, Ambient Layup: [90] <sub>16</sub>	SACMA SRM 1R-94	Strength <sup>(2)</sup> : Min. Ind. $\geq 61.5$ ksi Strength <sup>(2)</sup> : Average $\geq 73.0$ ksi Modulus <sup>(2)(4)</sup> : 7.92 to 9.52 msi, avg
0° (Warp) Short Beam Strength, Room Temperature, Ambient Layup: [0] <sub>33</sub>	ASTM D2344	Strength: Min. Ind. $\geq 9.90$ ksi Strength: Average $\geq 11.30$ ksi

(1) Specific procedures should be identical to those used in the original material qualification program.

(2) Normalize the properties to a cured ply thickness value of 0.0079 inch, based on theoretical nominal CPT, using the following equation:

$$\text{Normalized\_Value} = \text{Measured\_Value} \times \text{Measured\_CPT} / \text{Nominal\_CPT}$$

(3) "ind." refers to individual measurements. "avg." refers to the average of 5 replicates. Limits computed at  $\alpha=0.01$  and modified CV.

(4) Modulus range must be linear and calculated using 1000 to 3000 microstrain.

## QUALIFIED PRODUCTS LIST

Supplier Product Designation	Supplier Name and Production Location	Date Qualified	Specification Callout <sup>(1)</sup>
Syensqo EP2190 T650 PW	Supplier Name: Syensqo Composite Materials  Production Location: Abenbury Way Wrexham Industrial Estate Wrexham Clwyd – LL13 9UZ United Kingdom	9/18/2025	NMS 219/2  Classification callout is optional because Type 37, Class 2, Form 4, Grade 193 is the only classification allowed in this QPL.

<sup>(1)</sup> In accordance with NCAMP Standard Operating Procedures, NSP 100, this QPL shall not contain alternate materials/products. Additional production location may be included in the QPL only after successful equivalency demonstration and approval per NCAMP Prepreg Process Control Document (PCD) Preparation and Maintenance Guide, NRP 101.

<sup>(1)</sup> The proper specification callout for material procurement purpose is “NMS 219/2.” This specification is developed based on the material properties that are available publicly. The purchaser may specify additional requirements beyond those specified in this specification, especially when the purchaser has generated additional material properties beyond those available publicly or when the application requires additional requirements. The additional requirements are subject to supplier review and approval.